

WHAT IS CLAIMED:

1. A lamella positionable in a headbox of a web production machine, said lamella being formed of at least one high-performance polymer; and
said at least one high-performance polymer comprising high stability, high heat resistance, and good to very good resistance to at least one of alkaline solution and acid.
2. The lamella in accordance with claim 1, wherein said high-performance polymer has a tensile strength R_m (DIN 53455) in the range of about 50 N/mm² to about 150 N/mm², and a breaking elongation A_s (DIN 53455) in the range of about 20 % to about 80 %.
3. The lamella in accordance with claim 2, wherein said tensile strength R_m is in a range of about 70 N/mm² to about 110 N/mm², and said breaking elongation A_s is in a range of about 30 % to 60 %.
4. The lamella in accordance with claim 1, wherein said high-performance polymer has a modulus of elasticity E (DIN 53457, ISO 527-2) in a range of about 500 N/mm² to about 10,000 N/mm².
5. The lamella in accordance with claim 4, wherein said modulus of elasticity E is in a range of about 1,000 N/mm² to about 5,000 N/mm².
6. The lamella in accordance with claim 1, wherein said high-performance polymer has an impact strength when notched (ISO 179) of about 40 kJ/m² to about 100 kJ/m².
7. The lamella in accordance with claim 6, wherein said impact strength is in a range of about 45 kJ/m² to about 90 kJ/m².
8. The lamella in accordance with claim 1, wherein said high-performance polymer has a moisture acceptance FA (ISO 62) in the range of about 0.05 % to about 2 %.

9. The lamella in accordance with claim 8, wherein said moisture acceptance FA is in a range of about 0.2 % to about 1.2 %.

10. The lamella in accordance with claim 1, wherein said high-performance polymer has a heat resistance WB (DIN 53461) in the range of about 120°C to about 230°C.

11. The lamella in accordance with claim 10, wherein said heat resistance WB is in a range of about 170°C to about 220°C.

12. The lamella in accordance with claim 1, wherein said high-performance polymer has a low swelling Q in a range of about 0.02 % to about 0.2 %.

13. The lamella in accordance with claim 12, wherein said low swelling Q is a low linear swelling Q_L .

14. The headbox in accordance with claim 1, wherein said high-performance polymer comprises at least one of polyphenylene sulphone (PPSU), polyether sulphone (PES), polyetherimide (PEI), and polysulphone (PSU).

15. The lamella in accordance with claim 1, further comprising a nozzle, and said lamella includes a free end arranged to extend to a region of said nozzle, wherein said free end comprises an structure less end region with a dull lamella end having a height less than about 0.4 mm.

16. The lamella in accordance with claim 15, wherein said height of said dull lamella end is less than about 0.3 mm.

17. The lamella in accordance with claim 1, further comprising a nozzle, and said lamella includes a free end arranged to extend to a region of said nozzle, wherein said free end comprises structured end region with a dull lamella end having a height of more than about 0.5 mm.

18. The lamella in accordance with claim 17, wherein said structured end region comprises grooves having at least one of:

(A) at least one of essentially rectangular, wedge-shaped, parabolic, and essentially round structure, and

(B) varying depth.

19. The lamella in accordance with claim 17, wherein at least said lamella end is constructed of said at least one high-performance polymer.

20. The lamella in accordance with claim 1, wherein said lamella is constructed of said high-performance polymer in a homogenous structure.

21. The lamella in accordance with claim 1 in combination with a headbox with a sectioned fiber suspension density control, wherein said lamella is located within said headbox.

22. The lamella in accordance with claim 1 in combination with a headbox designed for a jet speed greater than about 1,500 m/s.

23. The lamella in combination with said headbox in accordance with claim 22, wherein the jet speed is greater than about 1,800 m/s.

24. The lamella in accordance with claim 1 in combination with a multi-layered headbox, wherein said lamella is integrated into said multi-layered headbox as a separating lamella.

25. The lamella in accordance with claim 1, wherein the web production machine comprises one of a paper, cardboard, and tissue machine.

26. A headbox of a web production machine comprising:
a lamella formed of at least one high-performance polymer,
wherein said at least one high-performance polymer comprises high stability, high heat resistance, and good to very good resistance to at least one of alkaline solution and acid.

27. The headbox in accordance with claim 26, wherein the web production machine comprises one of a paper, cardboard and tissue machine.